



AKFIX SLT21 EPOXY COATING (TRANSPARENT)

1 – PRODUCT DESCRIPTION

Akfix SLT21, is a two component, solvent free, self leveling, epoxy coating designed for high build decorative coatings and decorative quartz/flake applications. Akfix SLT21 is ideal as a clear top coat over decorative quartz or vinyl flake floor broad cast systems.

2 – FEATURES & BENEFITS

- Solvent free, 100% solid
- Attractive, high gloss, reflective coating
- High impact resistance
- Durable, impermeable and seamless
- Excellent mechanical properties

3– APPLICATION AREAS

Typical applications may include:

- Offices and laboratories
- Museums and galleries
- Auto dealerships
- 3D decorative applications

4 – SURFACE PREPARATION & APPLICATION PROCEDURE

Surface Preparation: Surface must be clean, sound and dry. Remove dust, laitance, grease, curing compounds, preparation bond inhibiting impregnations, waxes and any other contaminants. All projections, rough spots, etc. should be removed to achieve a level surface prior to the application.

Mixing: Pour Component B (hardener) into the Component A (resin) pail and mix using a low speed (300rpm) electric drill until mixture is completely homogenous. Be careful not to introduce any air bubbles while mixing. Make sure the contents are completely mixed to avoid any weak or partially cured spots in the coating. During the mixing operation, scrape down the sides and bottom of the container with a flat or straight edge trowel at least once to ensure complete mixing.

Application Method: Akfix SLT21 applied with a 10 - 20 mils (0.25 - 0.50 mm) notched squeegee over a smooth surface and a flat squeegee over a rough or decorative quartz surface. . Back roll the product only to level the squeegee applied material. Over-rolling and late back rolling may cause bubbling and leave roller marks.

Important: Application on wet and frozen surfaces should not be done. Substrate moisture content and also adherence should be checked before application. Epoxy based products have limited working time. Pot life and curing time will be shorter at high temperatures and also will be longer at low temperatures. Especially in hot environments, mixture should be applied immediately and should not be left in the mixture box. The mixture that started to gel should not be applied to the surface. Mixture other than the specified mixture ratio should not be done.



TECHNICAL DATA SHEET

Akfix® coating

Yeşilbayır Mah. Şimşir Sk. No: 22 Hadımköy - İstanbul/TÜRKİYE Tel: 0212 771 13 71 Fax: 0212 771 38 88

www.akfixcoating.com - info@akfixcoating.com

5- PACKAGING

Component A: 10 Kg (Epoxy Resin) Component B: 5 Kg (Hardener)

6- SHELF LIFE & STORAGE CONDITIONS

Akfix SLT21 can be kept for minimum 12 months in the original unopened pails at a temperature of 5 °C - 25 °C in dry places.

7- TECHNICAL FEATURES

	METHOD	DATAS
Mix Ratio	-	2:1
Viscosity (Mixture)	ASTM D2196-99	700 cps
Density (Component A)	EN ISO 2811-1	1,1 g/cm ³ (25°C)
Density (Component B)	EN ISO 2811-1	1,02 g//cm ³ (25°C)
Density (Mixture)	EN ISO 2811-1	1,08 g/cm ³ (25°C)
Pot Life	INTERNAL	45 min. (23 °C 50% R.H.)
Tack Free Time	INTERNAL	4 hours (23 °C 50% R.H.)
Light Traffic Time	INTERNAL	24 hours (23 °C 50% R.H.)
Full Cure Time	INTERNAL	7 days (23 °C 50% R.H.)
Shore D Hardness	ASTM D2240	80 (After 7 days)
Shrinkage	INTERNAL	0 %
Adhesion strength	ASTM D4541	>3N/mm ² (Concrete)
UV Resistance	ASTM G23	Color stable, no crack or blister (1000 hr)
Application Temperature	-	10 °C- 35 °C

DISCLAIMER

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.